

RESPIREX TESTING LABORATORY

Unit F, Kingsfield Business Centre, Philanthropic Road, Redhill, Surrey RH1 4DP

Tel: +44 (0) 1737 857391 Fax: +44 (0) 1737 779441 Email: laboratory@respirex.co.uk

Permeation Resistance Data for Material A00037 PVC C2

Challenge Chemical Hydrofluoric acid 71-75% CAS No 7664-39-3

Normalised breakthrough time (ASTM F739) 38 minutes

Normalised breakthrough time (EN ISO 6529) 42 minutes



Helen Keogh
Laboratory Manager
Respirex Testing Laboratory



RESPIREX™

Respirex International Ltd